

PRODUCT SPECIFICATION

Product Group: Genus Eco Liner and Fluting Medium

An engineered cluster of container board economically designed to fulfil the strength necessity of corrugated board. Made out of state of art machineries and process, delivered after stringent quality checks.

GSM	140	180	200	230
Conditioned Basis Weight (7.5%Moisture) TAPPI T 410				
Nominal	140	180	200	230
Lower Guide	133	171	190	219
Upper Guide	147	189	210	242
Burst Factor * (±1)	Ring Crush Test – CD **, kN/m			
TAPPI T 807	TAPPI T 822			
18	0.80	1.00	1.20	1.40
20	0.90	1.10	1.30	1.60
22	1.10	1.60	1.80	1.90
25	1.20	1.75	1.90	2.30
28	1.40	1.85	2.05	2.55
Moisture Content, % - TAPPI T 412				
Average	8.00	8.00	8.00	8.00
Range (+/-)	1.50	1.50	1.50	1.50
Cobb-60Seconds(g/m2) - TAPPI T 441				
Target	50	50	50	50
Range (±)	10	10	10	10
** RCT Tolerance ± 10 %				
* Burst Factor Tolerance ± 1				

*per TAPPI standard condition of 23±1 Degree C and 50±2 % RH.